

# Figure 4™ HI TEMP 300-AMB

High Temperature

Industry-leading, ultra-high temperature resistant rigid plastic suitable for the harshest thermal environments

Figure 4®

## HIGH THERMAL-RESISTANCE, TRANSLUCENT AMBER PLASTIC FOR FLOW VISUALIZATION (HDT >300 °C)

Figure 4 HI TEMP 300-AMB is an ultra-high temperature plastic for use in applications requiring high heat resistance. It is the industry's highest heat resistant material with heat deflection temperature of over 300 °C at both low and high stress (at 0.455 and 1.82 MPa). This material is well suited for the testing of high temperature components in applications including HVAC, consumer appliances, motor enclosures, stators, molds, and the like. It does not require a secondary thermal post-cure.

### Liquid Material

LIQUID PROPERTIES			
MEASUREMENT	CONDITION	METRIC	U.S.
Viscosity	@ 25 °C (77 °F)	1725 cps	4170 lb/ft-hr
Color		Amber	
Liquid Density	@ 25 °C (77 °F)	1.19 g/cm <sup>3</sup>	0.043 lb/in <sup>3</sup>
Package Volume		1 kg bottle - Figure 4 Standalone 2.5 kg cartridge - Figure 4 Modular 10 kg container - Figure 4 Production	
Layer Thickness (Standard Mode)		0.05 mm	0.002 in
Vertical Build Speed (Standard Mode)		36 mm/hr	1 in/hr
Draft Mode		40 mm/hr	1.6 in/hr

## APPLICATIONS


- High temperature components testing and general use parts including: HVAC, consumer appliances, motor enclosures, stators, etc.
- Low pressure molding/tooling: expanding foams, rubbers, etc.
- Overmolding

## BENEFITS

- Production-grade material
- High heat resistance for testing and use in high heat environments
- No secondary thermal post-cure required
- Excellent visualization for parts requiring evaluation of internal features and fluid flow performance

## FEATURES

- HDT over 300 °C at both low and high stress (HDT at 0.455 and 1.82 MPa)
- Rigid and translucent
- High tensile modulus for use in molds (4000 MPa)



## Post-Cured Material

MECHANICAL PROPERTIES			
MEASUREMENT	CONDITION	METRIC	U.S.
Solid Density (g/cm <sup>3</sup>   lb/in <sup>3</sup> )	ASTM D792	1.3	0.047
Tensile Strength, Ultimate (MPa   PSI)	ASTM D638	81	11750
Tensile Modulus (MPa   KSI)	ASTM D638	4000	580
Elongation at Break	ASTM D638	2.6%	
Flexural Strength (MPa   PSI)	ASTM D790	140	20305
Flexural Modulus (MPa   KSI)	ASTM D790	4260	618
Notched Izod Impact Strength (J/m   Ft-lbs/in)	ASTM D256	10	0.2
Unnotched Izod Impact Strength (J/m   Ft-lbs/in)	ASTM D4812	138	2.6
Heat Deflection Temperature @ 0.455 MPa (66 PSI) @ 1.82 MPa (264 PSI)	ASTM D648	>300 °C > 300 °C	>570 °F > 570 °F
Coefficient of Thermal Expansion (CTE) (ppm/°C   ppm/°F) 0-100 °C 150-250 °C	ASTM E831	62 54	34 30
Hardness, Shore	ASTM D2240	89D	
Water Absorption (24 hour)	ASTM D570	0.36%	



\* Note: Not all products and materials are available in all countries – please consult your local sales representative for availability.

[www.solidline.de](http://www.solidline.de)

[3d-druck@solidline.de](mailto:3d-druck@solidline.de)

0800 76 54 396

Warranty/Disclaimer: The performance characteristics of these products may vary according to product application, operating conditions, or with end use. 3D Systems makes no warranties of any type, express or implied, including, but not limited to, the warranties of merchantability or fitness for a particular use. © 2019 by 3D Systems, Inc. All rights reserved. Specifications subject to change without notice. 3D Systems, the 3D Systems logo and Figure 4 are registered trademarks of 3D Systems, Inc.